



COMPOSITION	53% polyester, 47% FR polyester	
WIDTH	218cm	
WEIGHT	253gsm	
PATTERN REPEAT	H 15.5cm V 12cm	
ROLL SIZE	50m approx.	
CARE CODE	FR Polyester HealthCare	
LIGHTFASTNESS AS 2001.4.21	6	
FIRE RATINGS AS/NZS 1530.3	Ignitability	0
	Spread of Flame	0
	Heat Evolved	0
	Smoke Developed	1
APPLICATION	curtains, privacy screens, bedspreads	

PERFORMANCE

- Easy to wash, quick drying with minimal shrinkage.
- Designed to withstand hospital and healthcare laundry and performance standards:
- AS/NZS 4146 Australian and New Zealand Standard for Laundry Practice.
- AS3789.9 Textiles for healthcare facilities and institutions: Curtains and patient bedscreens: fabric performance properties for colourfastness.
- AS2663.1 Textiles - fabrics for window furnishings: Uncoated fabrics - dimensional change.

ENVIRONMENT + GREEN STAR

- Environmentally Improved Production Process: reduced water (40%) and energy consumption, recycling of waste (70%).
- Manufacturer has Environmental Policy and is a member of Australian Greenhouse Challenge.
- MEMPHIS can be used on white furniture certified to Ecospecifier, AFRDI, ECNZ and GECA.
- The Green Star Rating Tool states “Where at least 90% of an item’s mass is certified to a GBCA recognised standard, the item can be entered as a certified product at Level A, B or C.” Therefore any fabric can be used, as fabrics are almost always under 10% by weight of a furniture item.

LAUNDRY GUIDELINES FOR THERMAL DISINFECTION

Laundry Sorting

- Wash separately. Do not wash with cotton articles.
- Colours, whites and heavily soiled articles should be washed separately.

Washing

- Use a reduced load (approx 1/2 of usual).
- Break wash 59-68°F (15-20°C) for 3 minutes with detergent (Do not wash with soap).
- Main wash 167-176°F (75-80°C) for 12 minutes with detergent as above.
- A chlorine based disinfectant may be used.

Rinsing

- Rinse thoroughly.
- Avoid crash cooling which causes excessive and permanent creasing.
- Rinse a second time with cold water.
- Do not use softener or fabric conditioner without prior testing its effect on flame retardant fabrics.

Drying

- Short tumble dry - Max 176°F (80°C).
- Do not overdry as this causes static.
- For calendaring ensure articles have a residual moisture of 20 – 30%.
- Keep dry wash below 248°F (120°C) on calender.